## **EUROPEAN PATENT OFFICE**

NTFT

PTFT

## **Patent Abstracts of Japan**

**PUBLICATION NUMBER** 

11317530

**PUBLICATION DATE** 

16-11-99

APPLICATION DATE

22-02-99

**APPLICATION NUMBER** 

11043976

APPLICANT:

SEMICONDUCTOR ENERGY LAB CO

LTD:

INVENTOR: YAMAZAKI SHUNPEI:

INT.CL.

: H01L 29/786 H01L 21/336 G02F 1/136

TITLE

SEMICONDUCTOR DEVICE

ABSTRACT :

PROBLEM TO BE SOLVED: To enable a semiconductor device of high performance to be manufactured at a low temperature, by a method wherein an intrinsic non-single crystal semiconductor layer is formed on a silicon oxide film through a vacuum CVD method where disilane or trisilane is used, the intrinsic non-single crystal semiconductor layer is heated at a specific temperature to turn crystalline, and a gate insulating film is formed on the semiconductor layer.

SOLUTION: A silicon oxide film is formed as a blocking layer 51 on a glass 50, and a silicon film is formed thereon using disilane or trisilane through a vacuum CVD method. In this case, this process is carried out, for instance, at a temperature of 530°C lower than a crystallization point. Then, an amorphous silicon film is formed and thermally treated at an intermediate temperature lower than 700°C, for instance, at a temperature of 450 to 700°C in a non-oxidizing atmosphere. Through this annealing process, the silicon film is transformed from an amorphous structure to another structure of high order and partially turned into a crystalline state. A silicon oxide film is formed thereon as a gate insulating film.

COPYRIGHT: (C)1999,JPO